



AUTEX 2018
Leading Edge Technologies
and Trends in Textiles

18th World
Textile Conference

www.autex2018.org

BOOK OF ABSTRACT

20-22 June 2018

Swiss Hotel Bosphorus
Istanbul, Turkey

Dalya



Experimental analysis of cotton based textile surface modification influence on wear comfort

I Bake¹, B Lukasevica¹, S Vihodceva¹, Z Zelca¹ and S Kukle¹

¹Riga Technical University, Material Science and Applied Chemistry Faculty, Institute of Design Technology, Kipsalas Street 6, room 218. Riga LV-1048, Latvia
Ieva.Bake@edu.rtu.lv

Extended abstract content

This research focuses on multifunctional surface nano-coatings of cotton and cotton/polyamide textiles and impact estimation onto such day-to-day wear comfort properties as air permeability, thermal and vapour resistance, as well wearer perceptions and sensory evaluation of comfort.

Silica sol with TEOS precursor modified with the 7.5 wt% zinc acetate dihydrate [1] was used to modify organic cotton (81%) and polyamide (19%) blend yarn knitted socks, net cotton jersey and double jersey knitwear. The high UV protection ability and anti-microbial activity of functionalized cotton fabric samples, as well improved wear resistance attained by the used sol-gel process is discussed in previous publications [1-4].

The goal of this research is to adapt developed sol-gel process to knitwear assortment worn as a base layer or first to the body cloth layer.

The surface wettability of socks examined by the water contact angle measurement shows good water repellence of three samples after hydrothermal treatment (marked W) with consolidation temperature varying in range from 100 to 120°C and consolidation time 8 minutes (Fig.1). At the same time before first hydrothermal treatment water contact angles are much lower for all three variants. Drop of vapour permeability in a range from 1.5% (W100/8) to 9% (W120/5) and air permeability drop down from 4.2% (W120/8) to 19.5% (W100/8) shows that combination of consolidation temperature 120°C and 8 minutes processing time, for modification of socks with applied sol, is more favorable.




Figure 1. Water contact angle of modified and subjected to following hydrothermal treatment socks

100 volunteers of different age (Fig. 2) were engaged in the experimental wear, of whom 85 wore cotton T-shirts subjected to the processing, 15 respondents wore unprocessed ones. 66% of wearers perceived differences between unprocessed and sol-gel treated T-shirts and 26% noticed lack of sweat odour (Fig.4).




Figure 2. Age distribution of volunteers




Figure 3. User perceived benefits

Increased resistance to dirt and need for less frequent washing, are the main advantages, named by T-shirt wearers (Fig. 3). Those, who are working ten and more hours, greatly appreciated all three mentioned benefits. Proposed applications ranged by experimental users shown in Figure 5




Figure 4. User observations




Figure 5. Distribution of T-shirt usage

Acknowledgments

This work has been supported by the European Social Fund within the Project “Synthesis of textile surface coating modified in nano-level and energetically independent measurement system integration in smart clothing with functions of medical monitoring” Nr.1.1.1.1./16/A/020 (PVS ID 2588).

References

- [1] Vihodceva S *Extension of the range of textiles modified at nano-level*. Summary of the Doctoral Thesis. Riga Technical University, 2014
- [2] Vihodceva S, Kukle S *Improvement of UV protection properties of the textile from natural fibres by the sol-gel method* Journal IOP Conference Series: Material Science Engineering. 2013. Vol 49. pp. 1-4
- [3] Vihodceva S, Kukle S and Muter O. *Antimicrobial Properties of the Modified Cotton Textiles by the Sol-Gel Technology* Advanced Materials Research. 2015. Vol 1117. pp. 213-216.
- [4] Kukle S, Vihodceva S, Beļakova D, Lukaševiča B, Riepniece A. At the Nano-level Modified Cotton Knitwear Prototype Development. In: *AUTEX 2017 Conference Proceedings: IOP Conference series*, 2017, pp.1-5.

Corresponding author:

Name: BAKE

Riga Technical University, Material Science and Applied Chemistry Faculty, Institute of Design
Technology

E-mail: Ieva.Bake@edu.rtu.lv